

Synthetic Enamel

<Product Information>

Description:

A high quality synthetic industrial gloss enamel paint. This product is especially used for industrial equipment which resists to oil, rust, gasoline and other chemical products.

Physical constants:

Color:	All RAL
Specific gravity	1.2 kg/l
Viscosity:	90 Kus
Pigments:	Titanium dioxide
Binder:	Synthetic resin
PVC:	27%
Flash point:	35 C
Packing:	1 or 5 US gallons

Regulations:

Labeling is required in accordance with the Federal German Regulation of Dangerous Substances dated August 26, 1986.
If contact with eyes, wash with plenty of water.

Application instructions:

Nb. Of coats:	2 coats for maximum uniformity and color retention
Type of application:	spraying
Thinner:	35% suitable thinner
Coverage:	40-45 SQ-M per US gallon
Drying time:	25min

Surface preparation:

All surfaces should be clean, dry, free from oil, grease, dirt, as well as deteriorated or peeling paints. For newly painted surfaces, the following application should be made:

Steel: Prime with TONACO paint for galvanized steel

Metal: Prime with synthetic Zinc Phosphate primer

Precaution of safety:

Labeling is required with accordance with the German federal regulation of dangerous substance.

R-phrases:

- | | |
|----------|--|
| 20 | Harmful by inhalation |
| 36/37/38 | Irritating to eyes and respiratory systems and skin. |
| 42 | may cause sensitization by inhalation |

S-phrases:

- | | |
|-----|--|
| 7/8 | Keep container tightly closed and dry |
| 26 | In case with contacts with eyes, rinse immediately with plenty of water. |
| 38 | In case of insufficient ventilation wear suitable respiratory equipment. |